

# FIBRANGyps JF 120



## Product Description

Joint filler in powder to be mixed with water for manual application, long setting time.  
3B CE marked according to UNI EN 13963.

## Applications

Bedding compound and finishing, suitable as a first-and secondhand.

Features	U. M.	Value	Standard
Reaction to fire	Class	A1	EN 13501-1
Weight	kg/m <sup>3</sup>	825 ± 25	-
Density dried product	kg/m <sup>3</sup>	1050 ± 50	-
Workable time	min	120	EN 13963
Setting time	min	315	EN 13963
Performance	kg/m <sup>3</sup>	0,39	-
Preparation	-	Manual mixing with clean tools	-
Rating water/powder	-	60/40	-

## Storage and Application

Store in a cool, dry, ventilated and protected area. Use within 12 months from the date of production. Do not use at temperatures below + 5 ° C and above + 35 ° C.

FIBRAN reserves the right to alter or amend product specifications without notice. The information included in this publication is correct to the best of our knowledge at the time of printing. Whilst FIBRAN will endeavor to ensure publications are up to date, it is the user's responsibility to check with the company the validity of the information prior to materials' use. For more information visit the web site [www.fibran.it](http://www.fibran.it).

Date 31/07/2018