


FIBRANgyps A



Product Description

Gypsum based board (plasterboard) standard type A , CE marked according to the standard UNI EN 520, with one decorative ivory face .

Available with tapered edge in three different thickness : 9,5mm(BA10), 12,5mm(BA13), 15mm (BA15), 18mm (BA18).

Applications

Suitable for installation with metal stud of partitions, lining systems and ceilings.

Features	U. M.	Value	Standard
Edge	-	BA tapered edge	EN 520
Width	mm	1200 or 1250	EN 520
Thermal conductivity (at 10°C)	W/m K	$\lambda_d = 0,25$ theoretical value	EN 10456
Reaction to fire	Class	A2-s1,d0	EN 520
Specific Heat Capacity	kJ/kg K	$c_p = 1,0$ theoretical value	EN 10456
Water vapor resistance factor	-	$\mu = 10$ in dry area theoretical value	EN 10456

Type	Thickness [mm]	Weight [kg/m ²]	Length [m]	Flex. long. [N]	Flex. trasv. [N]
BA10	9,5	7,7	2,0-2,5-3,0	≥ 400	≥ 160
BA13	12,5	9,2	2,0-2,5-2,6-2,7-2,8-3,0-3,2	≥ 550	≥ 210
BA15	15	12,9	2,0-2,5-2,6-2,7-2,8-3,0	≥ 650	≥ 250
BA18	18	15,5	2,6	≥ 774	≥ 303

Marking on the board back:

FIBRANgyps A – sp.12,5mm - CE – A - EN 520 A2-S1,d0(B) - date and time of production- D.o.P number.

FIBRAN reserves the right to alter or amend product specifications without notice. The information included in this publication is correct to the best of our knowledge at the time of printing. Whilst FIBRAN will endeavor to ensure publications are up to date, it is the user's responsibility to check with the company the validity of the information prior to materials' use. For more information visit the web site www.fibran.it .

Date 31/07/2018

FIBRAN S.p.A. via Fiasella 5/11 16121 GENOVA Italy - ph. +39 010 25466.1 fax +39 010 25466.949 - www.fibran.it – tech@fibran.it